

AWTA TEXTILE TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Textile Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT : INTERFACE AUSTRALIA PTY LTD
4 HENRY STREET
PICTON NSW 2571

TEST NUMBER : 7-550993-AN
DATE : 02/03/2007
ORDER NUMBER : 18315

SAMPLE DESCRIPTION Clients Ref: "Cubic & Cubic Colours"
Loop pile tufted carpet tile
Colour: Grey
Approximate pile height: 3.0mm

Material Specification:
Nominal Composition: 100% nylon
Nominal Total Pile Mass: 610g/m²
Nominal Backing: Glasbac

ASISO 9239.1-2003
Part 1

Reaction to Fire Tests for Floorings
Determination of the Burning Behaviour
using a Radiant Heat Source

Date of sample arrival: 08.02.2007
Date tested: 01.03.2007
Results:

CHF (Critical Heat Flux / Critical Radiant Flux)

	1	2	3	Mean	
Length	5.4	4.9	5.2	5.2	kW/m ²
Width	5.4	-	-	-	kW/m ²

	1	2	3	Mean	
Length	219	168	185	191	% min
Width	188	-	-	-	% min

Observations: Melting
Blistering

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing

158831

2

(CONTINUED NEXT PAGE)

PAGE 1

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
- Chemical Testing of Textiles & Related Products : Accreditation No. 983
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985
- Heat & Temperature Measurement : Accreditation No. 1356

The tests reported herein have been performed in accordance with its terms of accreditation. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced, in whole or in part, without the written consent of AWTA Ltd. This document, the names AWTA Textile Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

